

Test	Unit of Measurement	80	90	95/50	70
Shore Hardness A or D	Sh A / D	80 A ± 5	90 A ± 5	95 A/ 50 D ± 5	70 D ± 5
Density	g / cm ³	1,1	1,1	1,1	1,1
Tensile Strength	N / mm ²	25	30	35	36
Elongation at Rupture	%	700	400	400	250
Elongation at Rupture	N/mm	65	70	85	90
Flexibility	%	70	45	40	35
Tension at 100% Elongation	N / mm ²	3	7,5	12,5	35
Tension at 300% Elongation	N / mm ²	4,4	14,5	23,4	-
Wear Loss	mm ³	48	50	65	65